

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>5</sup> :</b> <b>C01F 17/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 95/03252</b> <b>(43) International Publication Date:</b> 2 February 1995 (02.02.95)
<b>(21) International Application Number:</b> PCT/US94/08162 <b>(22) International Filing Date:</b> 20 July 1994 (20.07.94)  <b>(30) Priority Data:</b> 08/095,749                      21 July 1993 (21.07.93)                      US  <b>(71) Applicant:</b> RODEL, INC. [US/US]; 451 Bellevue Road, Newark, DE 19713 (US). <b>(72) Inventor:</b> ANG, Jiun-Fang; 5 White Briar Circle, Hockessin, DE 19707 (US). <b>(74) Agent:</b> BENSON, Kenneth, A.; P.O. Box 191, Chatham, PA 19318 (US).		<b>(81) Designated States:</b> CN, JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> OXIDE PARTICLES AND METHOD FOR PRODUCING THEM  <b>(57) Abstract</b>  The invention is a process for preparing chemically active solid oxide particles useful for polishing, composed primarily of CeO <sub>2</sub> , or CeO <sub>2</sub> together with other oxides, comprising: (a) forming an aqueous solution comprising: (a) of a water soluble trivalent cerium salt and an oxidizing agent, and (b) aging said mixture in the liquid state for a time not less than 4 hours.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

OXIDE PARTICLES AND METHOD FOR PRODUCING THEM

5

## BACKGROUND OF THE INVENTION

Technical   ld

The invention is a process for preparing chemically  
10 active solid oxide particles useful for polishing,  
composed primarily of  $\text{CeO}_2$ , or  $\text{CeO}_2$  together with  
other oxides, which consists of mixing an aqueous  
solution of a water soluble trivalent cerium salt  
together with an oxidizing agent and aging said  
15 mixture in the liquid state for a time not less than  
4 hours.

Background Art

The particles of the invention are useful for the  
20 polishing of glass and other silica or silicon  
containing articles. The polishing process consists  
of the controlled abrasion of a solid surface by a  
suspension of small solid abrasive particles which is  
pressed against the substrate surface by a rotating  
25 viscoelastic pad. While, in principle, slurries of  
any particles may be used to polish a surface, in  
practice, only specific classes of particles have  
been shown to exhibit polishing rates which are high  
enough to be economically useful. Chemically active  
30 polishing compounds are restricted to a small class  
of oxides, particularly,  $\text{CeO}_2$ ,  $\text{ZrO}_2$ ,  $\text{Fe}_2\text{O}_3$  and  $\text{SnO}_2$ .  
Of these oxides,  $\text{CeO}_2$  has by far the highest  
polishing activity, and is the preferred basis of the

vast majority of commercially available polishing slurries.

The above oxides have been shown to require specific  
5 activation sequences before high rates of polishing  
are observed. Specifically, all known prior art  
polishing compounds require calcination, i.e. a  
roasting of previously prepared solid particles at  
some temperature below the sintering point of the  
10 oxide, to produce the desired activity. While it is  
recognized that a partial reason for the calcination  
is the conversion of solid starting compounds (e.g.  
carbonates, oxalates, nitrates or sulphates) to the  
corresponding oxide, specific sintering temperatures  
15 not directly related to the conversion have been  
demonstrated to have a pronounced effect on rate of  
polishing.

While calcination is universally practiced in the  
20 manufacture of polishing compounds, it is  
disadvantageous for several reasons. First, gaseous  
byproducts are produced which in some cases can be  
toxic or corrosive ( $\text{CO}$ ,  $\text{NO}_x$ ,  $\text{HF}$ ,  $\text{SO}_3$ ). Second,  
calcination is energy intensive and relatively  
25 expensive. Third, exposure to furnace environments  
leads to the contamination of the polishing compound  
by furnace refractories or environmental debris which  
may degrade polishing performance due to scratch  
formation by the foreign material.

30

The most significant difficulty caused by the  
calcination process is that products must be milled  
after calcination to yield particle size

distributions in the final product which are sufficiently small to prevent scratching. Particles above a critical diameter produce a scratched rather than a polished surface. While this is less critical for coarse polishing processes, production of critical optical surfaces, semiconductor wafers and integrated circuits requires a complete freedom from surface defects, achievable only when particle size distributions fall below 1 micron. Production of such distributions by conventional milling techniques is extremely difficult and often not economically feasible.

To date, the only technique which has been shown to produce solid oxides directly from solution is hydrothermal synthesis. In this process, amorphous metal hydrous oxides are held at elevated temperature and pressure for varying times to produce small particles of the solid oxide in the final solution. While the process has been extensively investigated for use in structural ceramics as in U. S. Patent No. 4619817, there has been no indication of its utility in preparing polishing compounds. To date, only two publications have disclosed methods for preparing  $\text{CeO}_2$  particles via hydrothermal synthesis. They are:

Hsu et al, (Langmuir vol. 4, pp.31-7, 1988), aged extremely dilute ( $10^{-4}$  molar) solutions of ceric sulphate at low pH (0.5-2.0) at  $90^\circ\text{C}$  to yield submicron particles of cubic  $\text{CeO}_2$  which were contaminated with varying amounts of sulphate. No effort was made to evaluate polishing activity. The

extremely low starting concentrations make such a synthesis economically infeasible.


Grahl-Madsen and Riman (Proc. 3rd Int. Conf. on Ceramic Powder Science, pp. 33-40, 1990) described the incorporation of cerium into zirconium oxide powders prepared via hydrothermal synthesis. Trivalent cerium salts,  $\text{Ce}(\text{NO}_3)_3$ , were added to a basic (pH 9.5) solution of 1 molar  $\text{Zr}(\text{NO}_3)_2 \cdot \text{XH}_2\text{O}$  to form a gel which was then exposed to hydrothermal conditions (closed cell at  $250^\circ\text{C}$ ) for varying times so as to transform the gel into a crystalline oxide product. Pure cerium oxides were prepared using extremely dilute (0.016M) starting solutions of  $\text{Ce}(\text{NO}_3)_3$ . Cubic non-stoichiometric  $\text{CeO}_2$  products were produced which had a primary crystallite size of 40nm. The reaction mechanism proposed was the hydrothermal transformation of an amorphous hydrous oxide gel precursor into a solid crystalline oxide product. No polishing data were disclosed.

From the above, it is clear that a technique which produces solid oxide polishing compounds of appropriate size and polishing activity directly from solution at high solution concentration would be highly desirable, as almost all of the manufacturing steps currently required for production could be eliminated.


#### DESCRIPTION OF THE INVENTION

The process of the present invention is comprised of preparing a solution composed primarily of a water

soluble salt of trivalent cerium (e.g.  $\text{Ce}(\text{NO}_3)_3$ ) in water together with an oxidizing agent and aging the solution for a period of time sufficient to convert the starting materials to submicron particles of the solid oxide. Unexpectedly, water itself has been shown to be a sufficient oxidizing agent, following the reaction:



However, other oxidizing agents, particularly hydrogen peroxide may be added yielding a reaction mechanism of:



The formation of both hydrogen and protons as reaction products on aging is a characteristic of syntheses of the present invention. One may optionally add bases, buffers or substances reactive to free hydrogen to further modify the course of the reaction. One can improve yields of  $\text{CeO}_2$  by neutralizing resulting protons, thus driving the reactions to the right, modify the  $\text{Ce}^{3+}/\text{Ce}^{4+}$  ratio in the resulting product by altering the redox equilibria during the reaction, eliminate the possibility of flame or explosion due to the formation of free hydrogen reaction products by reacting or burning off the hydrogen or provide solutions of varying pH following the completion of the conversion to the oxide, again by controlling the proton concentration in the reaction products.

An additional feature of the present invention is that, optionally, the products of the present invention can be re-treated using fresh trivalent

salt solutions so as to produce crystals of appreciably larger size than can be produced in a single step synthesis. This permits a wide variety of particle sizes to be produced for various applications, e.g., grinding abrasives.

Another feature of the invention is that, optionally, one may add non-cerium compounds to the aqueous solution so that particles of other oxides such as  $\text{ZrO}_2$ ,  $\text{Fe}_2\text{O}_3$  and  $\text{SnO}_2$  might be formed along with the  $\text{CeO}_2$  particles.

While apparently similar, this invention differs substantially from the mechanism set forth by Grahl-Madsen and Riman. They propose a mechanism whereby an initial amorphous  $\text{Ce}^{4+}$  hydrous oxide gel is converted to the crystalline oxide by exposure to elevated temperatures and pressures, at or above  $250^\circ\text{C}$ . In contrast, we have shown that the reaction mechanism is substantially more complex, consisting of a significant redox reaction which results in the production of hydrogen gas as the crystalline oxide is produced. A recognition of the redox nature of the reaction allows many additional refinements as outlined above. The ability to control crystal stoichiometry is believed to be particularly significant, as the introduction of a controlled non-stoichiometry during synthesis will result in the formation of a controlled level of lattice defects in the resulting crystals, an effect which is believed to have a positive effect on the polishing activity. Thus control of non-stoichiometry should allow control of the uniformity of polishing rates in



resulting products. High yields of crystalline  $\text{CeO}_2$  can be produced at room temperature or temperatures well below the boiling point of water, making practical synthesis of solid oxides appreciably easier and less expensive.

### EXAMPLES

Drying of solutions in the following Examples was carried out at ambient temperature and pressure.

Example 1: Solutions with 0.06 mol and 0.12 mol of  $\text{Ce}(\text{NO}_3)_3$  were prepared using reagent grade  $\text{Ce}(\text{NO}_3)_3$ , deionized water and 28%  $\text{NH}_4\text{OH}$ . The pH was adjusted to about 9.5 with the 28%  $\text{NH}_4\text{OH}$ . After reaction at 210–250°C for 24 hours in a closed container, the average crystallite size was measured via transmission electron microscopy as about 30 nm for the 0.06 mol solution and about 50 nm for the 0.12 mol solution. Both solutions produced off-white slurries which gave pale tan powders after drying. A polishing test was carried out using a combination of the two slurries at 1% by weight solids. The test showed about 1000 Angstroms/min removal rate on  $\text{SiO}_2$ .

Example 2. 70ml of solution with 0.06 mol of  $\text{Ce}(\text{NO}_3)_3$  were prepared using 15ml of 28%  $\text{NH}_4\text{OH}$  and deionized water. After reaction at 150°C for 24 hours in a closed container, an off-white slurry was produced which gave a pale tan powder after drying. The average crystallite size was about 40 nm.

Example 3. A solution was prepared as in Example 2 which was held at a reaction temperature of 75°C, rather than at 150°C as in Example 2. As determined by X-ray diffraction patterns, two different kinds of crystalline phases were formed. The majority was cubic ceria phase and a minor unidentified phase was also formed. The unidentified phase disappeared after further reaction at 200°C for 24 hours. An off-white slurry was formed which became a pale tan powder after drying. The average particle size was about 100 nm both before and after further reaction. Yield of product in mols versus mols of starting material was greater than 90%.

Example 4. A solution was prepared as in Example 2 in which the Ce(III) solution concentration was doubled to 0.12 mol. This solution was reacted at a temperature of 105°C for 24 hours. Only cubic phase ceria was detected in the product off-white slurry or the pale tan powder formed on drying. Again, the product yield in mols versus mol of starting material was greater than 90%.

Example 5. When H<sub>2</sub>O<sub>2</sub> was used as an oxidizing agent in the cerous salt solutions, crystallites of CeO<sub>2</sub> were formed at room temperature. When 3ml of 30% H<sub>2</sub>O<sub>2</sub> was diluted with 30ml of deionized water and mixed with 0.06 mol Ce(NO<sub>3</sub>)<sub>3</sub> followed by pH adjustment with 20 ml of 28% NH<sub>4</sub>OH to form a 70ml solution, the mixture generated heat and bubbles and a dark brown solution. After four hours of aging, powder formed from the solution on drying showed an average crystallite size of about 7 nm.

Example 6. When a solution similar to that of Example 5 was reacted at 150°C for 24 hours in a closed container, the resulting powder was creamy-yellow in cubic crystalline phase and had an average crystallite size of about 12 nm. The yield of product in mols versus mols of starting material was greater than 95%.

Example 7. A ceria slurry obtained from 0.06 mol cerous solution reacted at 150°C for 24 hours was used as seed particles for further reaction. The crystallite size of the seeds ranged from 10 to 30 nm. The slurry of seed particles was neutralized using 28% NH<sub>4</sub>OH and washed until the solution pH was about 7. The slurry of seed particles was then mixed with a cerous solution prepared using 30ml of deionized water, 0.06 mol of cerous salt and 15 ml of 28% NH<sub>4</sub>OH and then held at a reaction temperature of 110°C for 24 hours. The resulting slurry was off-white and yielded a pale tan powder on drying. The particles obtained were of cubic crystalline phase and showed an average particles size of greater than 100 nm.

25

30

Claims

1. A process for preparing chemically active solid  $\text{CeO}_2$  particles useful for polishing comprising: (a)  
5 forming an aqueous solution comprised of a water soluble trivalent cerium salt and an oxidizing agent and (b) aging said solution as a liquid phase for a time not less than 4 hours at which time said trivalent cerium salt has been oxidized to said  
10 chemically active solid  $\text{CeO}_2$  particles.
2. A process as set forth in claim 1. wherein said oxidizing agent consists of water and said aging is carried out at a temperature of  $100^\circ\text{C}$  or greater.  
15
3. A process as set forth in claim 1 wherein said oxidizing agent consists of hydrogen peroxide.
4. A process as set forth in claim 1 wherein bases or  
20 buffers are added to said solution before aging.
5. A process as set forth in claim 1 wherein said water soluble trivalent cerium salt is  $\text{Ce}(\text{NO}_3)_3$ .
- 25 6. A process as set forth in claim 1, 2, 3, 4 or 5 wherein a salt or salts other than cerium compounds are added to said solution before aging so that particles prepared are a mixture of oxides.
- 30 7. The submicron particles produced from the process as set forth in claim 1, 2, 3, 4 or 5.

8. The submicron particles produced from the process as set forth in claim 1, 2, 3, 4 or 5 wherein a salt or salts other than cerium compounds are added to said solution before aging so that particles prepared are a mixture of oxides.

10

15

20

25

30

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US94/08162

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(5) : C01F 17/00

US CL : 423/263, 592; 106/3

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 423/263, 592; 106/3

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched  
none

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
none

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, A, 4,942,697(KHALADJI ET AL)24 JULY 1990, ALL CLAIMS	1-8
A	US, A, 5,011,671(LE LOARER)30 APRIL 1991, ALL CLAIMS	1-8
A	US, A, 4,965,057(DAVID ET AL)23 OCTOBER 1990, ALL CLAIMS	1-8

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* "A"	Special categories of cited documents: document defining the general state of the art which is not considered to be of particular relevance	*T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*E	earlier document published on or after the international filing date	*X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*L	document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*O	document referring to an oral disclosure, use, exhibition or other means	
*P	document published prior to the international filing date but later than the priority date claimed	*Z document member of the same patent family

Date of the actual completion of the international search

14 SEPTEMBER 1994

Date of mailing of the international search report

26 SEP 1994

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

MELISSA BONNER

Telephone No. (703) 308-3817

Form PCT/ISA/210 (second sheet)(July 1992)\*